

(12) **UK Patent Application** (19) **GB** (11) **2 284 298** (13) **A**

(43) Date of Printing by UK Office 31.05.1995

(21) Application No 9500800.9

(22) Date of Filing 13.07.1993

(30) Priority Data

(31) 9215254 (32) 17.07.1992 (33) GB

(86) International Application Data
PCT/GB93/01456 En 13.07.1993

(87) International Publication Data
WO94/02965 En 03.02.1994

(51) INT CL⁶
H01L 41/09

(52) UK CL (Edition N)
H1E EB E5

(56) Documents Cited by ISA
EP 0137148 A US 4594526 A

(58) Field of Search by ISA
INT CL⁶ H01L

(71) Applicant(s)

Cookson Group Plc

(Incorporated in the United Kingdom)

130 Wood Street, LONDON, EC2V 6EQ,
United Kingdom

(72) Inventor(s)


Steven John Butcher
Donald Harry Maguire Kings
James David Hobby

(74) Agent and/or Address for Service

Boulton Wade Tennant
27 Fumival Street, LONDON, EC4A 1PQ,
United Kingdom

(54) Ceramic deflection device

(57) A monolithic ceramic device comprising an integral electrostrictive deflection element and a displacement sensor which device comprises two layers of an electrostrictive ceramic material with a central electrode sandwiched therebetween, the outer surfaces of each layer of the ceramic material having attached thereto at least one conducting electrode and means for applying a bias field across a single layer of the electrostrictive ceramic material.



GB 2 284 298 A

PCT


WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁵ : H01L 41/09</p>	<p>A1</p>	<p>(11) International Publication Number: WO 94/02965 (43) International Publication Date: 3 February 1994 (03.02.94)</p>
<p>(21) International Application Number: PCT/GB93/01456 (22) International Filing Date: 13 July 1993 (13.07.93) (30) Priority data: 9215254.5 17 July 1992 (17.07.92) GB (71) Applicant (for all designated States except US): COOKSON GROUP PLC [GB/GB]; 130 Wood Street, London EC2V 6EQ (GB). (72) Inventors; and (75) Inventors/Applicants (for US only) : BUTCHER, Steven, John [GB/GB]; 16 The Paddocks, Yarnton, Kidlington, Oxon OX5 1TF (GB). KINGS, Donald, Harry, Maguire [GB/GB]; Grange Farm, Station Road, Launton, Bicester, Oxon OX6 0DX (GB). HOBBY, James, David [GB/GB]; 12 Queen Elizabeth Close, Didcot, Oxon OX11 8TU (GB).</p>	<p>(74) Agent: BOULT, WADE & TENNANT; 27 Fumival Street, London EC4A 1PQ (GB). (81) Designated States: GB, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</p>	

(54) Title: CERAMIC DEFLECTION DEVICE



(57) Abstract

A monolithic ceramic device comprising an integral electrostrictive deflection element and a displacement sensor which device comprises two layers of an electrostrictive ceramic material with a central electrode sandwiched therebetween, the outer surfaces of each layer of the ceramic material having attached thereto at least one conducting electrode and means for applying a bias field across a single layer of the electrostrictive ceramic material.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NE	Niger
BE	Belgium	GN	Guinea	NL	Netherlands
BF	Burkina Faso	GR	Greece	NO	Norway
BG	Bulgaria	HU	Hungary	NZ	New Zealand
BJ	Benin	IE	Ireland	PL	Poland
BR	Brazil	IT	Italy	PT	Portugal
BY	Belarus	JP	Japan	RO	Romania
CA	Canada	KP	Democratic People's Republic of Korea	RU	Russian Federation
CF	Central African Republic	KR	Republic of Korea	SD	Sudan
CG	Congo	KZ	Kazakhstan	SE	Sweden
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovak Republic
CM	Cameroon	LU	Luxembourg	SN	Senegal
CN	China	LV	Latvia	TD	Chad
CS	Czechoslovakia	MC	Monaco	TG	Togo
CZ	Czech Republic	MG	Madagascar	UA	Ukraine
DE	Germany	ML	Mali	US	United States of America
DK	Denmark	MN	Mongolia	UZ	Uzbekistan
ES	Spain			VN	Viet Nam
FI	Finland				

CERAMIC DEFLECTION DEVICE

The present invention relates to a ceramic
5 deflection device and, in particular, to a method of
producing and operating a monolithic ceramic
deflection device and displacement sensor which does
not employ a piezoelectric sensor.

Ceramic bending devices utilizing the converse
10 piezoelectric effect are well known in the art. This
is the phenomenon by which an applied electric field
generates a proportional shape change in such
materials. Devices often take the form of so-called
bimorphs and multimorphs. The operating principle is
15 identical in both cases. Alternating layers of
piezoelectric ceramic are poled, usually in
antiparallel directions. The application of an
electric field induces a transverse compressive strain
in those layers having polar directions parallel to
20 the field, due to the piezoelectric coefficient d_{31}
of the piezoelectric ceramic material. Conversely,
transverse tensile strain is induced in layers poled
antiparallel to the applied field. The free end of
the device is deflected by an amount determined by the
25 magnitude of the applied field, d_{31} and various
geometrical factors. The displacement is reversed on
reversal of the field direction. It is usual to apply
the same electric field across all of the layers of
the device.

30 EP-A-0137148 describes such a piezoelectric
bimorph constructed from piezoelectric ceramic layers
which are poled. This device has the advantage of a
monolithic sensor enabling feedback control. The
piezoelectric sensor portion of the device operates
35 without the application of an externally applied
electric bias field. The device is made to bend by

the application of an electric field to the remainder. This places a stress on the sensor portion, causing current to flow which can be related to the displacement of the element.

5 GB-A-2006541 discloses a piezoelectric bimorph which has a pair of oppositely polarized piezoelectric elements bonded to a common substrate. A drive circuit applies a deflection voltage to each element in the same sense as the polarization of the element and thus avoids depolarization of the elements. The
10 device does not include a displacement sensor.

EP-A-0262637 discloses a piezoelectric bimorph device in which the piezoelectric ceramic layers are poled in the same direction and the application of an
15 electric field across each layer causes bending. The device does not include a displacement sensor.

Similar bending devices employing the electrostrictive effect are also known. Again, this is a field-induced shape change, although the effect
20 does not require the poled structure essential for piezoelectrics.

In one example, two ceramic layers are bonded, in such a way as to enable electrical contact, to the major surfaces of a metal shim and electrodes applied
25 to their opposite surfaces. The application of an electric field between the metal shim and the upper external electrode causes upwards deflection. This is explained by the transverse electrostrictive coefficient, M_{12} or Q_{12} , which places the upper
30 ceramic layer under compressive strain. The deflection obtained varies, amongst others, as a function of the square of the applied field and, therefore, reversal of the electric field direction induces identical upwards deflection.

35 When the electric field is applied between the metal shim and the lower electrode, downwards

deflection is produced, regardless of the field direction.

Since electrostriction is a quadratic effect, the above described device requires modification if linear, bi-directional deflection is required. This may be achieved by the application of a d.c. bias field, V_b , across each of the layers. The value of V_b is varied by equal but opposite amounts, δV , to generate the linear displacement.

10 The prior art ceramic bending devices suffer from certain disadvantages. Piezoelectric devices require poling, the process by which a strong d.c. bias field is applied prior to normal operation to align dipoles in the material. In the poled condition, there is a linear, but hysteretic, relationship between induced displacement and applied fields. Additionally, the poled structure is metastable, being randomized under the influence of time, temperature and electric field. These disadvantages of piezoelectric materials and devices apply equally to piezoelectric displacement sensors.

We have now developed an electrostrictive deflection element comprising an integral sensor and a method for the fabrication thereof.

25 Accordingly, the present invention provides a monolithic ceramic device comprising an integral electrostrictive deflection element and a displacement sensor which device comprises two layers of an electrostrictive ceramic material with a central electrode sandwiched therebetween, the outer surfaces of each layer of the ceramic material having attached thereto at least one conducting electrode and means for applying a bias field across a single layer of the electrostrictive ceramic material.

35 The central electrode of the deflection element of the present invention is generally connected to the

earth.

The electrostrictive deflection device and sensor of the present invention together form a monolithic element, i.e. the sensor is an integral part of the device rather than, for example, a bonded strain gauge or capacitive displacement sensor.

The present invention also includes within its scope a method for the fabrication of a monolithic element as defined above, which method comprises forming a sandwich of a central electrode between two layers of an electrostrictive ceramic material, the outer surface of each of the layers of the ceramic material having a conducting electrode formed thereon.

The monolithic ceramic device may be formed by bonding individual ceramic plates onto a metal substrate which forms the central electrode, for example by means of an adhesive, or by depositing the electrostrictive ceramic material onto the metal substrate. The electrodes may be attached to the outer surface of each layer of the electrostrictive ceramic material by electrodeposition or other methods known in the art. Alternatively, the monolithic device may be formed by the method of tape casting the ceramic material, electroding, forming a laminate and firing the structure, in a manner similar to that used in the production of multilayer ceramic capacitors.

The present invention also includes within its scope a method of operating an electrostrictive deflection element and displacement sensor as hereinbefore defined, which method comprises applying a potential to the conducting electrode on one layer of the electrostrictive ceramic material and applying a d.c. bias voltage to the conducting electrode on the other layer of the electrostrictive ceramic material, and measuring the charge. The charge, Q , which is generated by the sensor portion of the structure may

be measured by conventional techniques. The deflection of the electrostrictive deflection element may thus be controlled by a feedback mechanism.

The present invention will be further described
5 with reference to

Figures 1 to 4 of the accompanying drawings, in which;

Figure 1 is a schematic illustration of the device of the present invention;

10 Figure 2 is a schematic illustration of the device of the invention caused to deflect upwardly;

Figure 3 is a schematic illustration of the device of the invention caused to deflect downwardly; and

15 Figure 4 is a graph of the sensor output voltage against the applied voltage for the device as described in the Example.

Referring to the drawings, two layers of an electrostrictive ceramic material, 1 and 2 are bonded to a central electrode 3 which is connected to earth
20 at 4. Electrodes 5 and 6, are formed on the outer surfaces of layers 1 and 2. The device is clamped in position by means of clamps 7 and 8. The connections to the electrodes 5 and 6 are shown at 9 and 10, respectively.

25 As shown in Figure 2, the application of a potential V to the upper electrode 5 induces an upwards deflection of the device, due to the transverse electrostrictive effect. A d.c. bias voltage, V_b , is simultaneously applied to the lower
30 electrode 6 and causes the lower section of the device to act as a sensor, generating a charge flow which is proportional to the change in displacement. Under constant conditions, the magnitude of the current is dependent only upon the variation in deflection. This
35 technique can be employed to control the deflection by a feedback technique (not shown).

Referring to Figure 3, the situation is reversed with the potential V being applied to the lower electrode 6 and the d.c. bias voltage, V_b, being applied to the upper electrode 5.

5 Without the application of the d.c. bias across the upper or lower layer, the sensor portion of the device of the invention is inoperative. This feature differentiates the present invention from those deflection devices which employ piezoelectric sensors,
10 which operate without a d.c. bias.

The application of the d.c. bias field to the sensor portion of the device itself causes a deflection which opposes that generated by the deflecting portion. Consequently, the d.c. bias
15 voltage may be maintained at a relatively small value, typically about 20 V, to obtain large displacements. It follows, however, that the effective stiffness of the device, which is the resistance to deflection, can be controlled by variation of the d.c. bias, a larger
20 d.c. bias providing a greater resistance to deflection. This type of device may be used in active vibration control.

The present invention will be further described with reference to the following Example.

25

EXAMPLE

A device of the type as described with reference to Figure 1 of the accompanying drawings was prepared
30 from an electrostrictive material based on lead magnesium niobium titanate, $\text{Pb}(\text{Mg}_{1/3}\text{Nb}_{2/3})\text{O}_3\text{-PbTiO}_3$.

The fired device consisted of layers of the ceramic material approximately 200 μm thick, separated by a central palladium electrode.

35 Electrical contacts were made to the surfaces of the ceramic layers as shown in Figure 1. A d.c. bias

voltage of 15 V was applied to the ceramic layer chosen to operate as a sensor and a triangle wave drive voltage was applied to the ceramic layer chosen to operate as an actuator. Displacement of the actuator placed a stress on the sensor, causing the generation of a proportional output signal. The sensor output signal (in mV) is plotted in Figure 4 as a function of the voltage applied to the actuator. The response is electrostrictive in nature, as expected for the motion of the actuator. The offset in the response is a natural consequence of the application of the d.c. bias to the sensor portion and can be removed by the application of an equal d.c. bias offset to the actuator portion.

15

20

25

30

35

CLAIMS:

1. A monolithic ceramic device comprising an integral electrostrictive deflection element and a displacement sensor which device comprises two layers of an electrostrictive ceramic material with a central electrode sandwiched therebetween, the outer surfaces of each layer of the ceramic material having attached thereto at least one conducting electrode and means for applying a bias field across a single layer of the electrostrictive ceramic material.
2. A deflection element as claimed in claim 1 wherein the central electrode is connected to earth.
3. A method for the fabrication of a monolithic ceramic device as claimed in claim 1, which method comprises forming a sandwich of a central electrode between two layers of an electrostrictive ceramic material, the outer surface of each of the layers of the ceramic material having a conducting electrode formed thereon.
4. A method as claimed in claim 3 wherein individual ceramic plates are bonded to a metal substrate which forms the central electrode.
5. A method as claimed in claim 3 wherein the ceramic layers are formed by depositing the electrostrictive ceramic material onto the metal substrate.
6. A method as claimed in claim 3 wherein the monolithic device is formed by tape casting the ceramic material, electroding, forming a laminate and firing the structure.

7. A method of operating an electrostrictive deflection element and displacement sensor as claimed in claim 1, which method comprises applying a potential to the conducting electrode on one layer of the electrostrictive ceramic material and applying a d.c. bias voltage to the conducting electrode on the other layer of the electrostrictive ceramic material, and measuring the charge.

8. A method as claimed in claim 7 wherein the deflection of the electrostrictive deflection element is controlled by a feedback mechanism.

9. A method of controlling the resistance to deflection of an electrostrictive deflection element and sensing device as claimed in claim 1, which method comprises varying the d.c. bias voltage applied to the conducting electrode on one layer of the electrostrictive ceramic material, whilst applying a potential to the conducting electrode on the other layer of the electrostrictive ceramic material.

25

30

35

FIG. 1.




FIG. 2.






FIG. 3.



2 / 2

FIG. 4.



INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 93/01456A. CLASSIFICATION OF SUBJECT MATTER
IPC 5 H01L41/09

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 5 H01L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US,A,4 594 526 (NEC CORPORATION) 10 June 1986 see abstract; figure 2 ---	1
A	EP,A,0 137 148 (IBM) 17 April 1985 cited in the application see abstract; figure 3 -----	1

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

2 December 1993

Date of mailing of the international search report

27.12.93

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Peisers, L

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 93/01456

Parent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-4594526	10-06-86	JP-A- 59094103	30-05-84
EP-A-0137148	17-04-85	US-A- 4625176	25-11-86
		DE-A- 3475441	05-01-89
		JP-B- 1002898	19-01-89
		JP-C- 1520292	29-09-89
		JP-A- 60067866	18-04-85